Technical specification

Steenfabriek De Rijswaard B.V. De Rijswaard 2 NL-5308 LV AALST	Tel: +31 418 - 55 22 21 www.rijswaard.nl		Rijswaard facing bricks
Product name:	Sandstone VB EF	DR4BW	
Product group:	4. Yellow/Natural/Beige		
Type number:			
Dimensions:	EF (215x100x65)		U Clay masonry unit, Category I according to EN 771-1:2011 + A1:2015
Length:	211	mm	
Width:	101	mm	
Height:	65	mm	
Tolerance category:	T2		
Range category:	R1		
Gross density:	1450	kg/m3	
Mean compressive strength:	15	N/mm2	
Durability: **freeze/thaw resistance:**	F2		
Water absorption	≤ 22 %	m/md	
Initial rate of water absorption:	IW4 4 - n.v.t.	kg/(m2.min)	
Content of active soluble salts:	S2		
Reaction to fire:	A1		

The performance values stated in this document represent the declared characteristics of the product. Full details are provided in the Declaration of Performance (DoP) supplied upon delivery.

Technical specification

Steenfabriek De Rijswaard B.V. De Rijswaard 2 NL-5308 LV AALST	Tel: +31 418 - 55 22 21 www.rijswaard.nl		Rijswaard facing bricks
Product name:	Grey Stock	DR40B	
Product group:	3. Bronze/Grey/Mix		
Type number:			
Dimensions:	EF (215x100x65)		U Clay masonry unit, Category I according to EN 771-1:2011 + A1:2015
Length:	214	mm	
Width:	102	mm	
Height:	65	mm	
Tolerance category:	T2		
Range category:	R1		
Gross density:	1500	kg/m3	
Mean compressive strength:	15	N/mm2	
Durability: **freeze/thaw resistance:**	F2 (80)		
Water absorption	≤ 18 %	m/md	
Initial rate of water absorption:	IW3 1.5 - 4	kg/(m2.min)	
Content of active soluble salts:	S2		
Reaction to fire:	A1		

The performance values stated in this document represent the declared characteristics of the product. Full details are provided in the Declaration of Performance (DoP) supplied upon delivery.

RIJSWAARD® BAKSTEEN