# Technical specification

| | | | |
|---|---|---|---|
| Steenfabriek De Rijswaard B.V.<br>De Rijswaard 2<br>NL-5308 LV AALST | Tel: +31 418 - 55 22 21<br>www.rijswaard.nl | | Rijswaard<br>facing bricks |
| | | | |
| **Product name:** | Buff Handmade | DR3B | |
| **Product group:** | 4. Yellow/Natural/Beige | | |
| **Type number:** | | | |
| **Dimensions:** | EF (215x100x65) | | U<br>Clay masonry unit,<br>Category I<br>according to EN 771-1:2011<br>+<br>A1:2015 |
| **Length:** | 215 | mm | |
| **Width:** | 101 | mm | |
| **Height:** | 64 | mm | |
| **Tolerance category:** | T2 | | |
| **Range category:** | R1 | | |
| **Gross density:** | 1450 | kg/m3 | |
| **Mean compressive strength:** | 15 | N/mm2 | |
| **Durability:**<br>**freeze/thaw resistance:** | F2 | | |
| **Water absorption** | ≤ 22 % | m/md | |
| **Initial rate of water absorption:** | IW4 4 - n.v.t. | kg/(m2.min) | |
| **Content of active soluble salts:** | S2 | | |
| **Reaction to fire:** | A1 | | |

**The performance values stated in this document represent the declared characteristics of the product. Full details are provided in the Declaration of Performance (DoP) supplied upon delivery.**

# Technical specification

| | | | |
|---|---|---|---|
| Steenfabriek De Rijswaard B.V.<br>De Rijswaard 2<br>NL-5308 LV AALST | Tel: +31 418 - 55 22 21<br>www.rijswaard.nl | | Rijswaard<br>facing bricks |
| | | | |
| **Product name:** | Highcliffe HV EF | DR3BW | |
| **Product group:** | 4. Yellow/Natural/Beige | | |
| **Type number:** | | | |
| **Dimensions:** | EF (215x100x65) | | U<br>Clay masonry unit,<br>Category I<br>according to EN 771-1:2011<br>+<br>A1:2015 |
| **Length:** | 215 | mm | |
| **Width:** | 101 | mm | |
| **Height:** | 64 | mm | |
| **Tolerance category:** | T2 | | |
| **Range category:** | R1 | | |
| **Gross density:** | 1450 | kg/m3 | |
| **Mean compressive strength:** | 15 | N/mm2 | |
| **Durability:**<br>**freeze/thaw resistance:** | F2 | | |
| **Water absorption** | ≤ 22 % | m/md | |
| **Initial rate of water absorption:** | IW4 4 - n.v.t. | kg/(m2.min) | |
| **Content of active soluble salts:** | S2 | | |
| **Reaction to fire:** | A1 | | |

**The performance values stated in this document represent the declared characteristics of the product. Full details are provided in the Declaration of Performance (DoP) supplied upon delivery.**

# Technical specification

| | | | |
|---|---|---|---|
| Steenfabriek De Rijswaard B.V.<br>De Rijswaard 2<br>NL-5308 LV AALST | Tel: +31 418 - 55 22 21<br>www.rijswaard.nl | | Rijswaard<br>facing bricks |
| | | | |
| **Product name:** | Beige Handmade | DR57B | |
| **Product group:** | 4. Yellow/Natural/Beige | | |
| **Type number:** | | | |
| **Dimensions:** | EF (215x100x65) | | U<br>Clay masonry unit,<br>Category I<br>according to EN 771-1:2011<br>+<br>A1:2015 |
| **Length:** | 217 | mm | |
| **Width:** | 102 | mm | |
| **Height:** | 64 | mm | |
| **Tolerance category:** | T2 | | |
| **Range category:** | R1 | | |
| **Gross density:** | 1450 | kg/m3 | |
| **Mean compressive strength:** | 15 | N/mm2 | |
| **Durability:**<br>**freeze/thaw resistance:** | F2 | | |
| **Water absorption** | ≤ 22 % | m/md | |
| **Initial rate of water absorption:** | IW4 4 - n.v.t. | kg/(m2.min) | |
| **Content of active soluble salts:** | S2 | | |
| **Reaction to fire:** | A1 | | |

**The performance values stated in this document represent the declared characteristics of the product. Full details are provided in the Declaration of Performance (DoP) supplied upon delivery.**