Technical specification

Steenfabriek De Rijswaard B.V. De Rijswaard 2 NL-5308 LV AALST	Tel: +31 418 - 55 22 21 www.rijswaard.nl		Rijswaard facing bricks
Product name:	Mersea Handmade	DR61B	
Product group:	4. Yellow/Natural/Beige		
Type number:			
Dimensions:	EF (215x100x65)		U Clay masonry unit, Category I according to EN 771-1:2011 + A1:2015
Length:	215	mm	
Width:	101	mm	
Height:	64	mm	
Tolerance category:	T2		
Range category:	R1		
Gross density:	1450	kg/m3	
Mean compressive strength:	15	N/mm2	
Durability: **freeze/thaw resistance:**	F2		
Water absorption	≤ 22 %	m/md	
Initial rate of water absorption:	IW4 4 - n.v.t.	kg/(m2.min)	
Content of active soluble salts:	S2		
Reaction to fire:	A1		

The performance values stated in this document represent the declared characteristics of the product. Full details are provided in the Declaration of Performance (DoP) supplied upon delivery.

Technical specification

Steenfabriek De Rijswaard B.V. De Rijswaard 2 NL-5308 LV AALST	Tel: +31 418 - 55 22 21 www.rijswaard.nl		Rijswaard facing bricks
Product name:	Highcliffe HV EF	DR3BW	
Product group:	4. Yellow/Natural/Beige		
Type number:			
Dimensions:	EF (215x100x65)		U Clay masonry unit, Category I according to EN 771-1:2011 + A1:2015
Length:	215	mm	
Width:	101	mm	
Height:	64	mm	
Tolerance category:	T2		
Range category:	R1		
Gross density:	1450	kg/m3	
Mean compressive strength:	15	N/mm2	
Durability: **freeze/thaw resistance:**	F2		
Water absorption	≤ 22 %	m/md	
Initial rate of water absorption:	IW4 4 - n.v.t.	kg/(m2.min)	
Content of active soluble salts:	S2		
Reaction to fire:	A1		

The performance values stated in this document represent the declared characteristics of the product. Full details are provided in the Declaration of Performance (DoP) supplied upon delivery.