Technical specification

Steenfabriek De Rijswaard B.V. De Rijswaard 2 NL-5308 LV AALST	Tel: +31 418 - 55 22 21 www.rijswaard.nl		Rijswaard facing bricks
Product name:	Windsor Aqua	DR110B	
Product group:	5. Sterrewaard Red/Manganese		
Type number:			
Dimensions:	EF (215x100x65)		U Clay masonry unit, Category I according to EN 771-1:2011 + A1:2015
Length:	213	mm	
Width:	104	mm	
Height:	64	mm	
Tolerance category:	T2		
Range category:	R1		
Gross density:	1700	kg/m^3	
Mean compressive strength:	15	N/mm^2	
Durability: **freeze/thaw resistance:**	F2 (80)		
Water absorption	≤ 13 %	m/md	
Initial rate of water absorption:	IW3 1.5 - 4	$kg/(m^2.min)$	
Content of active soluble salts:	S2		
Reaction to fire:	A1		

This overview provides an indication of the product properties. The final specifications are stated in the Declaration of Performance (DoP), which is provided upon delivery.

RIJSWAARD® BAKSTEEN

Technical specification

Steenfabriek De Rijswaard B.V. De Rijswaard 2 NL-5308 LV AALST	Tel: +31 418 - 55 22 21 www.rijswaard.nl		Rijswaard facing bricks
Product name:	Whitchurch Aqua	DR14B	
Product group:	1. Red		
Type number:			
Dimensions:	EF (215x100x65)		U Clay masonry unit, Category I according to EN 771-1:2011 + A1:2015
Length:	213	mm	
Width:	101	mm	
Height:	64	mm	
Tolerance category:	T2		
Range category:	R1		
Gross density:	1600	kg/m3	
Mean compressive strength:	15	N/mm2	
Durability: **freeze/thaw resistance:**	F2 (80)		
Water absorption	≤ 14 %	m/md	
Initial rate of water absorption:	IW3 1.5 - 4	kg/(m2.min)	
Content of active soluble salts:	S2		
Reaction to fire:	A1		

The performance values stated in this document represent the declared characteristics of the product. Full details are provided in the Declaration of Performance (DoP) supplied upon delivery.

RIJSWAARD® BAKSTEEN