

Technical specification

Steenfabriek De Rijswaard B.V. De Rijswaard 2 NL-5308 LV AALST	Tel: +31 418 - 55 22 21 www.rijswaard.nl		Rijswaard facing bricks
Product name:	Orion Handmade	DR125B	
Product group:	5. Sterrewaard Red/Manganese		
Type number:			
Dimensions:	EF (215x100x65)		
Length:	215	mm	U Clay masonry unit, Category I according to EN 771- 1:2011 + A1:2015
Width:	104	mm	
Height:	65	mm	
Tolerance category:	T2		
Range category:	R1		
Gross density:	1700	kg/m3	
Mean compressive strength:	15	N/mm2	
Durability:			
freeze/thaw resistance:	F2 (80)		
Water absorption	≤ 13 %	m/md	
Initial rate of water absorption:	IW3 1.5 - 4	kg/(m2.min)	
Content of active soluble salts:	S2		
Reaction to fire:	A1		

The performance values stated in this document represent the declared characteristics of the product. Full details are provided in the Declaration of Performance (DoP) supplied upon delivery.



Technical specification

Steenfabriek De Rijswaard B.V. De Rijswaard 2 NL-5308 LV AALST	Tel: +31 418 - 55 22 21 www.rijswaard.nl		Rijswaard facing bricks
Product name:	Sagitta Handmade	DR105B	
Product group:	5. Sterrewaard Red/Manganese		
Type number:			
Dimensions:	EF (215x100x65)		
Length:	215	mm	U Clay masonry unit, Category I according to EN 771- 1:2011 + A1:2015
Width:	104	mm	
Height:	65	mm	
Tolerance category:	T2		
Range category:	R1		
Gross density:	1700	kg/m3	
Mean compressive strength:	15	N/mm2	
Durability:			
freeze/thaw resistance:	F2 (80)		
Water absorption	≤ 13 %	m/md	
Initial rate of water absorption:	IW3 1.5 - 4	kg/(m2.min)	
Content of active soluble salts:	S2		
Reaction to fire:	A1		

The performance values stated in this document represent the declared characteristics of the product. Full details are provided in the Declaration of Performance (DoP) supplied upon delivery.

